

# **Film Capacitors**

# EMI Suppression Capacitors (MKP)

 Series/Type:
 B32021 ... B32026

 Date:
 September 2014

© EPCOS AG 2015. Reproduction, publication and dissemination of this publication, enclosures hereto and the information contained therein without EPCOS' prior express consent is prohibited.

EPCOS AG is a TDK Group Company.



# **EMI suppression capacitors (MKP)**

#### Y2/300 V AC

#### B32021 ... B32026

### **Typical applications**

- Y2 class for interference suppression
- "Line to ground" applications.

# Climatic

- Max. operating temperature: 110 °C
- Climatic category (IEC 60068-1): 40/110/56

### Construction

- Dielectric: polypropylene (MKP)
- Plastic case (UL 94 V-0)
- Epoxy resin sealing (UL 94 V-0)

#### Features

- Very small dimensions
- Good self-healing properties
- High voltage capability
- RoHS-compatible
- Halogen-free capacitors available on request

# Terminals

- Parallel wire leads, lead-free tinned
- Special lead lengths available on request


## Marking

Manufacturer's logo, lot number, date code, rated capacitance (coded), capacitance tolerance (code letter), rated AC voltage (IEC), series number, sub-class (Y2), dielectric code (MKP), climatic category, passive flammability category, approvals.

### **Delivery mode**

Bulk (untaped) Taped (Ammo pack or reel) For taping details, refer to chapter "Taping and packing"

# **Dimensional drawing**



Dimensions in mm

Lead spacing <i>e</i> ±0.4	Lead diameter d <sub>1</sub> ±0.05	Туре
10	0.6	B32021
15 27.5	0.8	B32022 B32024
37.5	1.0	B32026

# Marking example (position of marks may vary):





KMK1546-A

KMK1547-B



Y2

B32021 ... B32026

# Y2/300 V AC

# Approvals

Approval marks	Standards	Certificate		
	EN 60384-14, IEC 60384-14	40018909		
18	UL1414, UL1283	E97863 / E157153		
c <b>911</b>	CSA C22.2 No. 1 / No. 8			
		(approved by UL)		
c <b>91</b> us	<b>UL 60384-14, CSA E60384-14</b>			

Notes:	Effective January 2014, only for EMI supression capacitors: – UL 60384-14 certification replaces both UL 1414 and UL 1283 standards. – CSA C22.2 No. 1 and CSA C22.s No. 8 are replaced by CSA E60384-14. – References like 1414, 1283 are removed from the capacitor marking
	Capacitors under UL1414, UL1283 produced during or before 2013, are accepted under UL scope.
	Capacitors under CSA C22.2 No.1 / No. 8 produced during or before 2013, are accepted under cUL scope.





# B32021 ... B32026

Y2/300 V AC

# Overview of available types

Lead spacing	10 mm	15 mm	22.5 mm	27.5 mm	37.5 mm
Туре	B32021	B32022	B32023	B32024	B32026
C <sub>R</sub> (μF)					
0.0010					
0.0015					
0.0022					
0.0033					
0.0047					
0.0056					
0.0068					
0.0082					
0.010					
0.015					
0.022					
0.033					
0.047					
0.056					
0.068					
0.082					
0.10					
0.15					
0.22					
0.33					
0.39					
0.47					
0.56					
0.68					
0.82					
1.0					



Y2

# Ordering codes and packing units

Lead spacing	C <sub>R</sub>	Max. dimensions	Ordering code	Straight	Straight	Straight
		$w \times h \times l$	(composition see	terminals,	terminals,	terminals,
mm	μF	mm	below)	Ammo	Reel	Untaped
				pack		
				pcs./MOQ	pcs./MOQ	pcs./MOQ
10	0.0010	$4.0\times \ 9.0\times 13.0$	B32021A3102+***	4000	6800	4000
	0.0015	$4.0\times~9.0\times13.0$	B32021A3152+***	4000	6800	4000
	0.0022	$4.0\times~9.0\times13.0$	B32021A3222+***	4000	6800	4000
	0.0033	$4.0\times~9.0\times13.0$	B32021A3332+***	4000	6800	4000
	0.0047	$5.0\times11.0\times13.0$	B32021A3472+***	3320	5200	4000
	0.0056	$5.0\times11.0\times13.0$	B32021A3562+***	3320	5200	4000
	0.0068	$5.0\times11.0\times13.0$	B32021A3682+***	3320	5200	4000
	0.0082	$6.0\times12.0\times13.0$	B32021A3822+***	2720	4400	4000
	0.010	$6.0\times12.0\times13.0$	B32021A3103M***	2720	4400	4000
15	0.010	$5.0\times10.5\times18.0$	B32022A3103+***	4680	5200	4000
	0.015	$6.0\times11.0\times18.0$	B32022A3153+***	3840	4400	4000
	0.022	$6.0 \times 12.0 \times 18.0$	B32022A3223M***	3840	4400	4000
	0.022	$7.0\times12.5\times18.0$	B32022B3223+***	3320	3600	4000
	0.033	$8.0 \times 14.0 \times 18.0$	B32022A3333+***	2920	3000	2000
	0.047	$8.5 \times 14.5 \times 18.0$	B32022A3473M***	2720	2800	2000
	0.047	$9.0\times17.5\times18.0$	B32022B3473+***	2560	2800	2000
	0.056	$9.0\times17.5\times18.0$	B32022A3563+***	2560	2800	2000
	0.068	$9.0\times17.5\times18.0$	B32022A3683M***	2560	2800	2000
	0.082	$11.0\times18.5\times18.0$	B32022A3823M***	-	2200	1200

MOQ = Minimum Order Quantity, consisting of 4 packing units.

Further intermediate capacitance values on request.

# Composition of ordering code

- + = Capacitance tolerance code:
  - $M = \pm 20\%$
  - $K = \pm 10\%$

- \*\*\* = Packaging code:
  - 289 = Straight terminals, Ammo pack
  - 189 = Straight terminals, Reel
  - 240 = Crimped down from lead spacing 10 mm to 7.5 mm, Ammo pack
  - 140 = Crimped down from lead spacing 10 mm to 7.5 mm, Reel
  - 255 = Crimped down from lead spacing 15 mm to 7.5 mm, Ammo pack
  - 155 = Crimped down from lead spacing 15 mm to 7.5 mm, Reel
  - 003 = Straight terminals, untaped (lead length 3.2  $\pm$ 0.3 mm)
  - 000 = Straight terminals, untaped (lead length 6 1 mm)



Y2

# B32021 ... B32026

Y2 / 300 V AC

# Ordering codes and packing units

Lead spacing	C <sub>R</sub>	Max. dimensions	Ordering code	Straight	Straight	Straight
		$w \times h \times I$	(composition see	terminals,	terminals,	terminals,
mm	μF	mm	below)	Ammo	Reel	Untaped
				pack		
				pcs./MOQ	pcs./MOQ	pcs./MOQ
22.5	0.047	$6.0\times15.0\times26.5$	B32023A3473+***	2720	2800	2880
	0.056	$6.0\times15.0\times26.5$	B32023A3563M***	2720	2800	2880
	0.068	$7.0\times16.0\times26.5$	B32023A3683+***	2320	2400	2520
	0.068	$7.5 \times 14.5 \times 26.5$	B32023B3683M***	2200	2000	2280
	0.082	$8.5 \times 16.5 \times 26.5$	B32023A3823+***	1920	2000	2040
	0.10	$8.5 \times 16.5 \times 26.5$	B32023A3104M***	1920	2000	2040
	0.10	$10.5\times16.5\times26.5$	B32023B3104+***	1560	1600	2160
	0.15	$10.5\times18.5\times26.5$	B32023A3154M***	1560	1600	2160
	0.15	$10.5\times20.5\times26.5$	B32023B3154+***	-	-	2160
	0.22	$12.0\times22.0\times26.5$	B32023A3224M***	-	-	1800
	0.22	$14.5 \times 29.5 \times 26.5$	B32023B3224+***	-	-	2160
	0.33	$14.5 \times 29.5 \times 26.5$	B32023A3334+***	-	-	2160
	0.39	$14.5 \times 29.5 \times 26.5$	B32023A3394M***	-	-	2160
27.5	0.15	$11.0\times19.0\times31.5$	B32024A3154+***	-	1400	1280
	0.22	$11.0\times19.0\times31.5$	B32024A3224M***	-	1400	1280
	0.22	$11.0\times21.0\times31.5$	B32024B3224+***	-	1400	1280
	0.33	$13.5\times23.0\times31.5$	B32024A3334M***	-	1000	1040
	0.33	$14.0\times24.5\times31.5$	B32024B3334+***	-	-	1040
	0.47	$15.0\times24.5\times31.5$	B32024A3474M***	-	-	960
	0.47	$16.0\times32.0\times31.5$	B32024C3474+***	-	-	880

MOQ = Minimum Order Quantity, consisting of 4 packing units. Further intermediate capacitance values on request.

## Composition of ordering code

- + = Capacitance tolerance code:
  - $M = \pm 20\%$
  - $K = \pm 10\%$

\*\*\* = Packaging code:

- 289 = Straight terminals, Ammo pack
- 189 = Straight terminals, Reel
- 240 = Crimped down from lead spacing 10 mm to 7.5 mm, Ammo pack
- 140 = Crimped down from lead spacing 10 mm to 7.5 mm, Reel
- 255 = Crimped down from lead spacing 15 mm to 7.5 mm, Ammo pack
- 155 = Crimped down from lead spacing 15 mm to 7.5 mm, Reel
- 003 = Straight terminals, untaped (lead length  $3.2 \pm 0.3 \text{ mm}$ )
- 000 = Straight terminals, untaped (lead length 6 1 mm)



# Y2

# Ordering codes and packing units

Lead spacing	C <sub>R</sub>	Max. dimensions	Ordering code	Straight	Straight	Straight
		$w \times h \times l$	(composition see	terminals,	terminals,	terminals,
mm	μF	mm	below)	Ammo	Reel	Untaped
				pack		
				pcs./MOQ	pcs./MOQ	pcs./MOQ
27.5	0.47	$18.0\times27.5\times31.5$	B32024B3474+***	-	-	800
	0.56	$16.0\times32.0\times31.5$	B32024A3564+***	-	-	880
	0.68	$18.0\times33.0\times31.5$	B32024B3684+***	-	-	800
	0.68	$19.0\times30.0\times31.5$	B32024A3684M***	-	-	720
	0.68	$21.0\times31.0\times31.5$	B32024C3684+***	-	-	720
	0.82	$22.0\times36.5\times31.5$	B32024A3824+***	-	-	640
	1.0	$22.0\times36.5\times31.5$	B32024A3105M***	-	-	640
37.5	0.33	$12.0\times22.0\times41.5$	B32026A3334+***	-	-	1620
	0.47	$14.0\times25.0\times41.5$	B32026A3474+***	_	—	1380
	0.56	$14.0\times25.0\times41.5$	B32026A3564M***	-	-	1380
	0.56	$16.0\times28.5\times41.5$	B32026B3564+***	-	-	800
	0.68	$16.0\times28.5\times41.5$	B32026A3684+***	-	-	800
	0.82	$16.0\times28.5\times41.5$	B32026A3824M***	-	-	800
	0.82	$18.0\times32.5\times41.5$	B32026B3824+***	-	-	720
	1.0	$18.0\times32.5\times41.5$	B32026A3105M***	-	-	720
	1.0	$20.0\times39.5\times41.5$	B32026B3105+***	-	-	640

MOQ = Minimum Order Quantity, consisting of 4 packing units. Further intermediate capacitance values on request.

### Composition of ordering code

+ = Capacitance tolerance code:

 $M = \pm 20\%$  $K = \pm 10\%$ 

- \*\*\* = Packaging code:
  - 289 = Straight terminals, Ammo pack
  - 189 = Straight terminals, Reel
  - 240 = Crimped down from lead spacing 10 mm to 7.5 mm, Ammo pack
  - 140 = Crimped down from lead spacing 10 mm to 7.5 mm, Reel
  - 255 = Crimped down from lead spacing 15 mm to 7.5 mm, Ammo pack
  - 155 = Crimped down from lead spacing 15 mm to 7.5 mm, Reel
  - 003 = Straight terminals, untaped (lead length 3.2  $\pm$ 0.3 mm)
  - 000 = Straight terminals, untaped (lead length 6 1 mm)





# B32021 ... B32026

# Technical data

Reference standard: IEC / UL 60384-14. All data given at T = 20 °C unless otherwise specified.

Rated AC voltage (IEC 60384-14)	300 V (50/60 Hz)
Maximum continuous DC voltage $V_{DC}$	1500 V
Maximum continuous AC voltage $V_{AC}$	480 V (50/60 Hz)
Max. operating temperature T <sub>op,max</sub>	+110 °C
DC test voltage	4000 V (C $\leq$ 0.33 $\mu F),$ 3700 V (C $>$ 0.33 $\mu F),$ 2 s

The repetition of this DC voltage test may damage the capacitor. Special care must be taken in case of use several capacitors in a parallel configuration.

Dissipation factor tan $\delta$ (in 10 <sup>-3</sup> )		$C_{R} \leq 0.33 \; \mu F$	C <sub>R</sub> > 0.33 μF
at 20 °C (upper limit values)	at 1 kHz	1	1
Insulation resistance R <sub>ins</sub>	$C_{\text{R}} \leq 0.33 \; \mu\text{F}$		$C_R > 0.33 \ \mu F$
or time constant $\tau = C_R \cdot R_{ins}$ at 100 V DC, 20 °C, rel. humidity $\leq$ 65% and for 60 s (minimum as-delivered values)	100 000 MΩ		30 000 s
Passive flammability category	В		
Capacitance tolerances (measured at 1 kHz)	±10% (K), ±20% (M)		

# Pulse handling capability

"dV/dt" represents the maximum permissible voltage change per unit of time for non-sinusoidal voltages, expressed in  $V/\mu s$ .

" $k_0$ " represents the maximum permissible pulse characteristic of the waveform applied to the capacitor, expressed in V<sup>2</sup>/µs.

Note:

The values of dV/dt and  $k_0$  provided below must not be exceeded in order to avoid damaging the capacitor.

# dV/dt and k<sub>0</sub> values

Lead spacing	10 mm	15 mm	22.5 mm	27.5 mm	37.5 mm
dV/dt in V/µs	800	600	500	400	300
k₀in V²/μs	677 000	508 000	423 000	338 000	254 000

# ⊗TDK



B32021 ... B32026 Y2 / 300 V AC



Y2

# B32021 ... B32026 Y2 / 300 V AC

# **Testing and Standards**

Test	Reference	Conditions of test		Performance requirements
Electrical Parameters	IEC 60384-14	Voltage Proof: Between terminals, 1500 V AC, 1 min. Terminals and enclosure: 2 V <sub>R</sub> + 1500 V AC Insulation resistance, R <sub>INS</sub> Capacitance, C Dissipation factor, tan δ		Within specified limits
Robustness of terminations	IEC 60068-2-21	Tensile strength (tes Wire diameter $0.5 < d_1 \le 0.8 \text{ mm}$ $0.8 < d_1 \le 1.25 \text{ mm}$	t Ua1) Tensile force 10 N 20 N	Capacitance and tan $\delta$ within specified limits
Resistance to soldering heat	IEC 60068-2-20, test Tb, method 1A	Solder bath temperature at $260 \pm 5$ °C, immersion for $10$ seconds		$\Delta C/C_0 \le 5\%$ tan $\delta$ within specified limits
Rapid change of temperature	IEC 60384-16	$T_A$ = lower category temperature $T_B$ = upper category temperature Five cycles, duration t = 30 min.		No visible damage $ \Delta C/C_0  \le 5\%$ tan $\delta$ within specified limits
Vibration	IEC 60384-14	Test $F_c$ : vibration sinusoidal Displacement: 0.75 mm Accleration: 98 m/s <sup>2</sup> Frequency: 10 Hz 500 Hz Test duration: 3 orthogonal axes, 2 hours each axe		No visible damage
Bump	IEC 60384-14	Test Eb: Total 4000 bumps with 400 m/s <sup>2</sup> mounted on PCB 6 ms duration		No visible damage $I\Delta C/C_0 I \le 5\%$ tan $\delta$ within specified limits
Climatic sequence	IEC 60384-14	Dry heat $- T_{B} / 16$ h. Damp heat cyclic, 1st cycle + 55 °C / 24h / 95% 100% RH Cold $- T_{A} / 2h$ Damp heat cyclic, 5 cycles + 55 °C / 24h / 95% 100% rh		No visible damage $ \Delta C/C_0  \le 5\%$ $ \Delta \tan \delta   \le 0.008,$ $C \le 1 \mu F$ $ \Delta \tan \delta   > 0.005,$ $C > 1 \mu F$ Voltage proof $R_{INS} \ge 50\%$ of initial limit



Y2

Damp Heat	IEC 60384-14	Test Ca	No visible damage
Steady State	120 00304-14	40 °C / 93% RH / 56 days	$I\Delta C/C_0 I \le 5\%$
Oleady Olale			$ \Delta \tan \delta  \le 0.008$ ,
			C ≤ 1 μF
			$ \Delta \tan \delta  > 0.005$ ,
			C > 1 µF
			Voltage proof
			$R_{INS} \ge 50\%$ of initial limit
Impulse test	IEC 60384-14	3 impulses	No visible damage
Endurance		$T_{B} / 1.7 V_{R} / 1000$ hours,	I∆C/C₀ I ≤ 10%
		1000 V <sub>rms</sub> for 0.1 s every hour	$I\Delta \tan \delta I \le 0.008$ ,
			C ≤ 1 µF
			l∆ tan δ I > 0.005,
			C > 1 μF
			Voltage proof
			$R_{INS} \ge 50\%$ of initial limit
Passive	IEC 60384-14	Flame applied for a period of time	В
flammability		depending on capacitor volume	
Active	IEC 60384-14	20 discharges at 2.5 kV + V <sub>R</sub>	The cheesecloth shall
flammability			not burn with a flame





# Mounting guidelines

# 1 Soldering

# 1.1 Solderability of leads

The solderability of terminal leads is tested to IEC 60068-2-20, test Ta, method 1.

Before a solderability test is carried out, terminals are subjected to accelerated ageing (to IEC 60068-2-2, test Ba: 4 h exposure to dry heat at 155 °C). Since the ageing temperature is far higher than the upper category temperature of the capacitors, the terminal wires should be cut off from the capacitor before the ageing procedure to prevent the solderability being impaired by the products of any capacitor decomposition that might occur.

Solder bath temperature	235 ±5 °C
Soldering time 2.0 ±0.5 s	
Immersion depth 2.0 +0/-0.5 mm from capacitor body or seating plane	
Evaluation criteria:	
Visual inspection	Wetting of wire surface by new solder $\geq$ 90%, free-flowing solder

# 1.2 Resistance to soldering heat

Resistance to soldering heat is tested to IEC 60068-2-20, test Tb, method 1A. Conditions:

Series		Solder bath temperature	Soldering time
MKT	boxed (except $2.5 \times 6.5 \times 7.2$ mm) coated uncoated (lead spacing > 10 mm)	260 ±5 °C	10 ±1 s
MFP MKP	(lead spacing > 7.5 mm)		
MKT	boxed (case $2.5 \times 6.5 \times 7.2$ mm)		5±1 s
МКР МКТ	(lead spacing $\leq$ 7.5 mm) uncoated (lead spacing $\leq$ 10 mm) insulated (B32559)		< 4 s recommended soldering profile for MKT uncoated (lead spacing $\leq$ 10 mm) and insulated (B32559)

# ⊗TDK

	B32021 B32026 Y2 Y2 / 300 V AC
300 °C 250 200 150 0 0 50 100 150	KMK1242-V 4 s 200 s 250
	►t
Immersion depth	2.0 + 0/-0.5 mm from capacitor body or seating plane
Shield Heat-absorbing board, $(1.5 \pm 0.5)$ mm thick, between capabody and liquid solder	
Evaluation criteria:	
Visual inspection	No visible damage
$\Delta C/C_0$	2% for MKT/MKP/MFP 5% for EMI suppression capacitors
tan δ	As specified in sectional specification





# 1.3 General notes on soldering

Permissible heat exposure loads on film capacitors are primarily characterized by the upper category temperature  $T_{max}$ . Long exposure to temperatures above this type-related temperature limit can lead to changes in the plastic dielectric and thus change irreversibly a capacitor's electrical characteristics. For short exposures (as in practical soldering processes) the heat load (and thus the possible effects on a capacitor) will also depend on other factors like:

- Pre-heating temperature and time
- Forced cooling immediately after soldering
- Terminal characteristics:
- diameter, length, thermal resistance, special configurations (e.g. crimping)
- Height of capacitor above solder bath
- Shadowing by neighboring components
- Additional heating due to heat dissipation by neighboring components
- Use of solder-resist coatings

The overheating associated with some of these factors can usually be reduced by suitable countermeasures. For example, if a pre-heating step cannot be avoided, an additional or reinforced cooling process may possibly have to be included.

EPCOS recommends the following conditions:

- Pre-heating with a maximum temperature of 110 °C
- Temperature inside the capacitor should not exceed the following limits:
  - MKP/MFP 110 °C
  - MKT 160 °C
- When SMD components are used together with leaded ones, the leaded film capacitors should not pass into the SMD adhesive curing oven. The leaded components should be assembled after the SMD curing step.
- Leaded film capacitors are not suitable for reflow soldering.

### **Uncoated capacitors**

For uncoated MKT capacitors with lead spacings  $\leq$ 10 mm (B32560/B32561) the following measures are recommended:

- pre-heating to not more than 110 °C in the preheater phase
- rapid cooling after soldering



B32021 ... B32026

## Y2 / 300 V AC

# Y2


# Application note for the different possible X1 / X2 positions

# In series with the powerline (i.e. capacitive power supply)

**Typical Applications:** 

- Power meters
- ECUs for white goods and household appliances
- Different sensor applications
- Severe ambient conditions

# **Basic circuit**



# **Required features**

- High capacitance stability over the lifetime
- Narrow tolerances for a controlled current supply

# **Recommended EPCOS product series**


- B3293\* (305 V AC) heavy duty with EN approval for X2 (UL Q1/2010)
- B3265\* MKP series standard MKP capacitor without safety approvals
- B3267\*L MKP series standard MKP capacitor without safety approvals

## In parallel with the powerline

Typical Applications:

Standard X2 are used parallel over the mains for reducing electromagnetic interferences coming from the grid. For such purposes they must meet the applicable EMC directives and standards.

# **Basic circuit**



# **Required features**

- Standard safety approvals (ENEC, UL, CSA, CQC)
- High pulse load capability
- Withstand surge voltages

## **Recommended EPCOS product series**

- B3292\*C/D (305 V AC) standard series, approved as X2
- B3291\* (330 V AC), approved as X1





## Cautions and warnings

- Do not exceed the upper category temperature (UCT).
- Do not apply any mechanical stress to the capacitor terminals.
- Avoid any compressive, tensile or flexural stress.
- Do not move the capacitor after it has been soldered to the PC board.
- Do not pick up the PC board by the soldered capacitor.
- Do not place the capacitor on a PC board whose PTH hole spacing differs from the specified lead spacing.
- Do not exceed the specified time or temperature limits during soldering.
- Avoid external energy inputs, such as fire or electricity.
- Avoid overload of the capacitors.

The table below summarizes the safety instructions that must always be observed. A detailed description can be found in the relevant sections of the chapters "General technical information" and "Mounting guidelines".

Торіс	Safety information	Reference chapter "General technical information"
Storage conditions	Make sure that capacitors are stored within the specified range of time, temperature and humidity conditions.	4.5 "Storage conditions"
Flammability	Avoid external energy, such as fire or electricity (passive flammability), avoid overload of the capacitors (active flammability) and consider the flammability of materials.	5.3 "Flammability"
Resistance to vibration	Do not exceed the tested ability to withstand vibration. The capacitors are tested to IEC 60068-2-6. EPCOS offers film capacitors specially designed for operation under more severe vibration regimes such as those found in automotive applications. Consult our catalog "Film Capacitors for Automotive Electronics".	5.2 "Resistance to vibration"





Торіс	Safety information	Reference chapter "Mounting guidelines"
Soldering	Do not exceed the specified time or temperature limits during soldering.	1 "Soldering"
Cleaning	Use only suitable solvents for cleaning capacitors.	2 "Cleaning"
Embedding of capacitors in finished assemblies	When embedding finished circuit assemblies in plastic resins, chemical and thermal influences must be taken into account. Caution: Consult us first, if you also wish to embed other uncoated component types!	3 "Embedding of capacitors in finished assemblies"

# **Design of EMI Capacitors**

EPCOS EMI capacitors use polypropylene (PP) film metalized with a thin layer of Zinc (Zn). The following key points have made this design suitable to IEC/UL testing, holding a minimum size.

- Overvoltage AC capability with very high temperature Endurance test of IEC60384-14 (3<sup>rd</sup> edition, 2005-07) / UL60384-14 (1st edition, 2009-04) must be performed at 1.25 × V<sub>R</sub> at maximum temperature, during 1000 hours, with a capacitance drift less than 10%.
- Higher breakdown voltage withstanding if compared to other film metallizations, like Aluminum. IEC60384-14 (3<sup>rd</sup> edition, 2005-07) / UL60384-14 (1st edition, 2009-04) establishes high voltage tests performed at 4.3 × V<sub>R</sub> -1 minute, impulse testing at 2500 V for C= 1 µF and active flammability tests.
- Damp heat steady state: 40 °C/ 93% RH / 56 days. (without voltage or current load)

# Effect of humidity on capacitance stability

Long contact of a film capacitor with humidity can produce irreversible effects. Direct contact with liquid water or excess exposure to high ambient humidity or dew will eventually remove the film metallization and thus destroy the capacitor. Plastic boxed capacitors must be properly tested in the final application at the worst expected conditions of temperature and humidity in order to check if any parameter drift may provoke a circuit malfunction.

In case of penetration of humidity through the film, the layer of Zinc can be degraded, specially under AC operation (change of polarity), accelerated by the temperature, provoking an increment of the serial resistance of the electrode and eventually a reduction of the capacitance value. For DC operation, the parameter drift is much less.

Plastic boxes and resins can not protect 100% against humidity. Metal enclosures, resin potting or coatings or similar measures by customers in their applications will offer additional protection against humidity penetration.





# Display of ordering codes for EPCOS products

The ordering code for one and the same product can be represented differently in data sheets, data books, other publications and the website of EPCOS, or in order-related documents such as shipping notes, order confirmations and product labels. **The varying representations of the ordering codes are due to different processes employed and do not affect the specifications of the respective products**. Detailed information can be found on the Internet under <u>www.epcos.com/orderingcodes</u>.



B32021 ... B32026

Y2/300 V AC

Y2

# Symbols and terms

Symbol	English	German
α	Heat transfer coefficient	Wärmeübergangszahl
$\alpha_{c}$	Temperature coefficient of capacitance	Temperaturkoeffizient der Kapazität
A	Capacitor surface area	Kondensatoroberfläche
βc	Humidity coefficient of capacitance	Feuchtekoeffizient der Kapazität
С	Capacitance	Kapazität
C <sub>R</sub>	Rated capacitance	Nennkapazität
$\Delta C$	Absolute capacitance change	Absolute Kapazitätsänderung
$\Delta C/C$	Relative capacitance change (relative	Relative Kapazitätsänderung (relative
	deviation of actual value)	Abweichung vom Ist-Wert)
$\Delta C/C_R$	Capacitance tolerance (relative deviation	Kapazitätstoleranz (relative Abweichung
	from rated capacitance)	vom Nennwert)
dt	Time differential	Differentielle Zeit
$\Delta t$	Time interval	Zeitintervall
$\Delta T$	Absolute temperature change	Absolute Temperaturänderung
	(self-heating)	(Selbsterwärmung)
∆tan δ	Absolute change of dissipation factor	Absolute Änderung des Verlustfaktors
$\Delta V$	Absolute voltage change	Absolute Spannungsänderung
dV/dt	Time differential of voltage function (rate	Differentielle Spannungsänderung
	of voltage rise)	(Spannungsflankensteilheit)
$\Delta V / \Delta t$	Voltage change per time interval	Spannungsänderung pro Zeitintervall
E	Activation energy for diffusion	Aktivierungsenergie zur Diffusion
ESL	Self-inductance	Eigeninduktivität
ESR	Equivalent series resistance	Ersatz-Serienwiderstand
f	Frequency	Frequenz
f <sub>1</sub>	Frequency limit for reducing permissible	Grenzfrequenz für thermisch bedingte
	AC voltage due to thermal limits	Reduzierung der zulässigen
		Wechselspannung
f <sub>2</sub>	Frequency limit for reducing permissible	Grenzfrequenz für strombedingte
	AC voltage due to current limit	Reduzierung der zulässigen
		Wechselspannung
f <sub>r</sub>	Resonant frequency	Resonanzfrequenz
F <sub>D</sub>	Thermal acceleration factor for diffusion	Therm. Beschleunigungsfaktor zur Diffusion
-	Devoting factor	
F <sub>T</sub>	Derating factor	Deratingfaktor
1	Current (peak)	Stromspitze
I <sub>C</sub>	Category current (max. continuous	Kategoriestrom (max. Dauerstrom)
	current)	



Y2

B32021 ... B32026

Y2/300 V AC

Symbol	English	German
I <sub>RMS</sub>	(Sinusoidal) alternating current,	(Sinusförmiger) Wechselstrom
	root-mean-square value	
i <sub>z</sub>	Capacitance drift	Inkonstanz der Kapazität
k <sub>0</sub>	Pulse characteristic	Impulskennwert
Ls	Series inductance	Serieninduktivität
λ	Failure rate	Ausfallrate
λο	Constant failure rate during useful	Konstante Ausfallrate in der
	service life	Nutzungsphase
$\lambda_{\text{test}}$	Failure rate, determined by tests	Experimentell ermittelte Ausfallrate
P <sub>diss</sub>	Dissipated power	Abgegebene Verlustleistung
P <sub>gen</sub>	Generated power	Erzeugte Verlustleistung
Q	Heat energy	Wärmeenergie
ρ	Density of water vapor in air	Dichte von Wasserdampf in Luft
R	Universal molar constant for gases	Allg. Molarkonstante für Gas
R	Ohmic resistance of discharge circuit	Ohmscher Widerstand des
		Entladekreises
Ri	Internal resistance	Innenwiderstand
R <sub>ins</sub>	Insulation resistance	Isolationswiderstand
R <sub>P</sub>	Parallel resistance	Parallelwiderstand
Rs	Series resistance	Serienwiderstand
S	severity (humidity test)	Schärfegrad (Feuchtetest)
t	Time	Zeit
Т	Temperature	Temperatur
τ	Time constant	Zeitkonstante
tan δ	Dissipation factor	Verlustfaktor
$\tan \delta_{D}$	Dielectric component of dissipation factor	Dielektrischer Anteil des Verlustfaktors
tan δ <sub>P</sub>	Parallel component of dissipation factor	Parallelanteil des Verlfustfaktors
tan δ <sub>s</sub>	Series component of dissipation factor	Serienanteil des Verlustfaktors
T <sub>A</sub>	Temperature of the air surrounding the component	Temperatur der Luft, die das Bauteil umgibt
T <sub>max</sub>	Upper category temperature	Obere Kategorietemperatur
T <sub>min</sub>	Lower category temperature	Untere Kategorietemperatur
t <sub>OL</sub>	Operating life at operating temperature and voltage	Betriebszeit bei Betriebstemperatur und -spannung
Top	Operating temperature	Beriebstemperatur
Τ <sub>B</sub>	Rated temperature	Nenntemperatur
T <sub>ref</sub>	Reference temperature	Referenztemperatur
t <sub>SL</sub>	Reference service life	Referenz-Lebensdauer



Y2

Symbol	English	German
V <sub>AC</sub>	AC voltage	Wechselspannung
Vc	Category voltage	Kategoriespannung
V <sub>C,RMS</sub>	Category AC voltage	(Sinusförmige)
		Kategorie-Wechselspannung
V <sub>CD</sub>	Corona-discharge onset voltage	Teilentlade-Einsatzspannung
$V_{ch}$	Charging voltage	Ladespannung
V <sub>DC</sub>	DC voltage	Gleichspannung
$V_{FB}$	Fly-back capacitor voltage	Spannung (Flyback)
Vi	Input voltage	Eingangsspannung
Vo	Output voltage	Ausgangssspannung
V <sub>op</sub>	Operating voltage	Betriebsspannung
V <sub>p</sub>	Peak pulse voltage	Impuls-Spitzenspannung
V <sub>pp</sub>	Peak-to-peak voltage Impedance	Spannungshub
V <sub>R</sub>	Rated voltage	Nennspannung
Ŷ <sub>R</sub>	Amplitude of rated AC voltage	Amplitude der Nenn-Wechselspannung
V <sub>RMS</sub>	(Sinusoidal) alternating voltage,	(Sinusförmige) Wechselspannung
	root-mean-square value	
V <sub>SC</sub>	S-correction voltage	Spannung bei Anwendung "S-correction"
$V_{sn}$	Snubber capacitor voltage	Spannung bei Anwendung
		"Beschaltung"
Z	Impedance	Scheinwiderstand
е	Lead spacing	Rastermaß



The following applies to all products named in this publication:

- 1. Some parts of this publication contain statements about the suitability of our products for certain areas of application. These statements are based on our knowledge of typical requirements that are often placed on our products in the areas of application concerned. We nevertheless expressly point out that such statements cannot be regarded as binding statements about the suitability of our products for a particular customer application. As a rule, EPCOS is either unfamiliar with individual customer applications or less familiar with them than the customers themselves. For these reasons, it is always ultimately incumbent on the customer to check and decide whether an EPCOS product with the properties described in the product specification is suitable for use in a particular customer application.
- 2. We also point out that in individual cases, a malfunction of electronic components or failure before the end of their usual service life cannot be completely ruled out in the current state of the art, even if they are operated as specified. In customer applications requiring a very high level of operational safety and especially in customer applications in which the malfunction or failure of an electronic component could endanger human life or health (e.g. in accident prevention or lifesaving systems), it must therefore be ensured by means of suitable design of the customer application or other action taken by the customer (e.g. installation of protective circuitry or redundancy) that no injury or damage is sustained by third parties in the event of malfunction or failure of an electronic component.
- 3. The warnings, cautions and product-specific notes must be observed.
- 4. In order to satisfy certain technical requirements, some of the products described in this publication may contain substances subject to restrictions in certain jurisdictions (e.g. because they are classed as hazardous). Useful information on this will be found in our Material Data Sheets on the Internet (www.epcos.com/material). Should you have any more detailed questions, please contact our sales offices.
- 5. We constantly strive to improve our products. Consequently, the products described in this publication may change from time to time. The same is true of the corresponding product specifications. Please check therefore to what extent product descriptions and specifications contained in this publication are still applicable before or when you place an order. We also reserve the right to discontinue production and delivery of products. Consequently, we cannot guarantee that all products named in this publication will always be available. The aforementioned does not apply in the case of individual agreements deviating from the foregoing for customer-specific products.
- Unless otherwise agreed in individual contracts, all orders are subject to the current version of the "General Terms of Delivery for Products and Services in the Electrical Industry" published by the German Electrical and Electronics Industry Association (ZVEI).
- 7. The trade names EPCOS, Alu-X, CeraDiode, CeraLink, CeraPlas, CSMP, CSSP, CTVS, DeltaCap, DigiSiMic, DSSP, FilterCap, FormFit, MiniBlue, MiniCell, MKD, MKK, MLSC, MotorCap, PCC, PhaseCap, PhaseCube, PhaseMod, PhiCap, PQSine, SIFERRIT, SIFI, SIKOREL, SilverCap, SIMDAD, SiMic, SIMID, SineFormer, SIOV, SIP5D, SIP5K, TFAP, ThermoFuse, WindCap are trademarks registered or pending in Europe and in other countries. Further information will be found on the Internet at www.epcos.com/trademarks.

# **Mouser Electronics**

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

# EPCOS:

<u>B32022A3103M289</u> <u>B32022A3563M</u> <u>B32022A3823M</u> <u>B32022B3223M</u> <u>B32022B3473M</u> <u>B32023A3104M189</u>
332023A3154M189 B32023A3224M B32023A3334K B32023A3334M B32023B3104M189 B32024B3224M000
332024B3334M000 B32024B3474M000 B32022A3103K000 B32026B3564M000 B32022A3153K000
332026B3824M000 B32022A3223M189 B32022A3333K000 B32023A3394M000 B32023A3473M000
332023A3563M000 B32023A3683M000 B32023A3823M000 B32023B3104K000 B32023B3104M000
332023B3104M289 B32023B3154M000 B32023B3224M000 B32023B3683M000 B32024A3105M000
332024B3684M000 B32024C3474M000 B32024C3684M000 B32026A3105M000 B32026A3334M000
332026A3474K000 B32026A3474M000 B32022A3563K000 B32026A3684M000 B32026B3105K000
332022B3223K000 B32022B3223M289 B32022B3473K000 B32023A3104M289 B32024A3154M000
332024A3334M000 B32024A3474M000 B32024A3684M000 B32024A3824M000

# EPCOS / TDK:

B32021A3102M B32021A3103M B32021A3103M289 B32021A3152M B32021A3222M B32021A3222M289
B32021A3332K B32021A3332M B32021A3332M189 B32021A3472M189 B32021A3562M B32021A3682K
B32021A3822M B32022A3103M B32022A3153M B32022A3223M B32022A3333M B32022A3473M
B32022A3683M B32023A3104M B32023A3154M B32021A3332M289 B32021A3472K000 B32021A3472K289
B32021A3562K000 B32021A3682M000 B32021A3682M289 B32021A3822K000 B32021A3102K000
B32021A3102M189 B32021A3102M289 B32021A3152K000 B32021A3152M289 B32021A3222K000
B32021A3222M189 B32021A3472M B32024A3564M B32022A3103K189 B32021A3472K189 B32022B3473K289
B32022B3223M189 B32021A3472M289 B32022A3333M189 B32022A3683M289 B32022A3473M189
B32024B3224K189 B32022A3223M289 B32021A3152M189 B32023A3563M289 B32022A3823M189
B32021A3222K289 B32022A3683M189 B32026A3564M B32021A3682K289 B32022A3153M289
B32023A3473M189 B32022B3473M189 B32021A3103M189 B32021A3332K289 B32021A3682M189
B32023A3473M289 B32023A3683K189 B32022A3473M289 B32021A3562K289 B32021A3102K189
B32022A3333M289 B32022B3223K289 B32023B3683M189 B32021A3222K189 B32021A3102K289
B32022A3103M189 B32023B3104K189 B32022B3473K B32024B3474K B32024B3684K