

# SBRS-(3X)G

## Dual Wall Adhesive-Lined Heat-Shrink Polyolefin Tubing

Adhesive lined heat shrink tubing with environmental sealing capability for a wide variety of electrical applications, including automotive and marine wire harness, wire splices, breakouts, and connector-to-cable transitions.



### Features

- 3:1 shrink ratio
- Low longitudinal shrinkage
- Flame retardant (out jacket only)
- Super sealing against water, moisture or other contaminates
- Continuous operating temperature:-45°C-125°C
- Shrink Temperature:125°C



### Dimensions

Size		Expanded	After Recovery			Standard Package
Inch	mm	Internal Diameter mm	Internal Diameter mm	Total Wall Thickness mm	Adhesive Thickness mm	Spool Length M/spool
3/32	2.4	2,4	0.8	0.85 ± 0.15	0.40 ± 0.10	200
1/8	3.2	3,2	1.0	0.95 ± 0.15	0.40 ± 0.10	200
3/16	4.8	4,8	1.6	1.10 ± 0.15	0.40 ± 0.10	100
1/4	6.4	6,4	2.2	1.20 ± 0.15	0.45 ± 0.12	100
5/16	7.9	7,9	2.7	1.35 ± 0.15	0.50 ± 0.12	100
3/8	9.5	9,5	3.2	1.45 ± 0.20	0.50 ± 0.12	50
1/2	12.7	12,7	4.2	1.70 ± 0.20	0.50 ± 0.12	1.22 OR 25M/Roll
5/8	15	15	5.2	1.80 ± 0.20	0.55 ± 0.15	1.22 OR 25M/Roll
3/4	19.1	19,1	6.3	2.00 ± 0.20	0.55 ± 0.15	1.22 OR 25M/Roll
1	25.4	25,4	8.5	2.10 ± 0.25	0.55 ± 0.15	1.22 OR 25M/Roll
1-1/4	30	30	10.2	2.20 ± 0.25	0.60 ± 0.15	1.22 OR 25M/Roll
1-1/2	39	39	13.5	2.40 ± 0.25	0.60 ± 0.15	1.22 OR 25M/Roll
2	50	50	17	2.70 ± 0.25	0.70 ± 0.15	1.22 OR 25M/Roll
5/2	64	64	21	3.00 ± 0.30	0.70 ± 0.15	1.22 OR 25M/Roll
3	75	75	25	3.00 ± 0.30	1.00 ± 0.20	1.22 OR 25M/Roll
7/2	90	90	30	3.00 ± 0.30	1.00 ± 0.20	1.22 OR 25M/Roll
4	100	100	34	3.00 ± 0.30	1.00 ± 0.20	1.22 OR 25M/Roll
5	125	125	42	3.00 ± 0.30	1.00 ± 0.20	1.22 OR 25M/Roll

### Technical Data

Property	Test Method	Standard
Tensile Strength(MPa)	ASTM D2671	≥10.4
Elongation(%)	ASTM D2671	≥300
Tensile Strength after aging (MPa)	UL224 158°CX168hr	≥7.3
Elongation after aging(%)	UL224 158°CX168hr	≥200
Flammability	ASTM D2671B	Self-extinguish within 30s
Dielectric strength(kv/mm)	IEC 60243	≥15
Volume resistivity(Ω.cm)	IEC 60093	≥1X10 <sup>14</sup>

### Hot Melt Adhesive Property

Property	Test Method	Standard
Water Absorption	ASTM D570	<0.2%
Softening Point(°C)	ASTM E28	90 ± 5
Strength of pearing(PE)	ASTM D 1000	120N/25mm
Strength of pearing(AL)	ASTM D 1000	80N/25mm